

Patent Application No. 10/712,196
Docket No. JSF02-0004

In the claims:

1. (Currently amended)

A method of manufacturing a plurality of micro
5 enclosures on a substrate wafer, comprising steps of:

(1) bonding a cap wafer to said substrate wafer with
an adhesive layer;

(2) patterning and etching said cap wafer and said
adhesive layer to form islands of layers of said cap wafer
10 and said adhesive layer on said substrate wafer; and

(3) depositing and patterning at least one metal
~~and/or insulator~~ layer on said islands to form a sidewall
around each of said islands.

15 2. (Previously presented)

The method of claim 1, further comprising the steps
of:

(1) patterning and etching etch access holes in said
cap wafer of said enclosures;

20 (2) removing said adhesive layer through said etch
access holes from said enclosures; and

(3) sealing said etch access holes with deposited
films.

25 3. (Canceled)

Patent Application No. 10/712,196
Docket No. JSF02-0004

4. (Original) The method of claim 1, wherein said etching is accomplished with high-density plasma that contains hydrogen or argon.

5 5. (Original) The method of claim 1, wherein said substrate wafer comprises one or more of following:

micro-electro-mechanical device,

polymeric sacrificial layer,

polymeric planarizing layer,

10 microelectronic circuit,

and electrical component,

prior to said bonding.

6. (Previously presented)

15 The method of claim 1, further comprising a step of depositing getters on said cap wafer prior to said step (1) of bonding a cap wafer to said substrate wafer with an adhesive layer and subsequent heat activation of said getters.

20

7. (Previously presented)

The method of claim 2, wherein said deposited films comprises gas gettering materials.

25 8. (Currently amended)

Patent Application No. 10/712,196
Docket No. JSF02-0004

The method of claim 7, wherein said gettering materials comprise ~~one or more of the following:~~

TiN_xO_y and/or

5

~~TiZr_x~~

TiN_x

10 9. (Canceled)

10. (Canceled)

11. (Withdrawn)

15 The method of claim 2, wherein in said sealing is done under controlled gas pressure environment comprising high vacuum or inert gas.

12. (Withdrawn)

20 The method of claim 2, wherein said enclosures form pressure transducers.

13. (Currently amended)

25 The method of claim 12, wherein said enclosures form vacuum or hermetic packaging for micro-electro-mechanical devices.

14. (Original)

AMENDMENT --

6

Patent Application No. 10/712,196
Docket No. JSF02-0004

The method of claim 2, wherein said removing said adhesive layer is by etching with oxygenated plasma.

15. (Currently amended)

5 Said etching in claim 14 ~~further~~ removes ~~any~~ organic polymer coating or sacrificial layer ~~present~~ in said enclosures.

16. (Canceled)

10

17. (Original)

The method of claim 1, wherein said depositing at least on metal layer is by physical vapor deposition, plating, electroplating, or chemical vapor deposition.

15

18. (Canceled)

19. (Withdrawn)

20 The method of claim 1, further comprises planarizing said substrate wafer prior to said bonding, comprising steps of:

coating said wafer with a thick epoxy layer;
curing said epoxy layer by heat or ultraviolet light; and
thinning said epoxy layer to the desired thickness by
25 lapping, grinding or polishing.

20. (Withdrawn)

Patent Application No. 10/712,196
Docket No. JSF02-0004

The method of claim 19, wherein said thick epoxy layer fills holes, cavities, troughs, or underside space of suspended structures.

5 21. (Withdrawn)

The method of claim 20, further comprising the step of placing said wafer under a vacuum during or after said coating.

10 22. (Canceled)

23. (Canceled)

24. (Canceled)

15

25. (Canceled)

26. (Canceled)

20 27. (Canceled)

28. (Original)

The method of claim 1, wherein said adhesive layer is disposed by spinning and said spinning is at speed of
25 between 1500 rpm to 7000 rpm for less than 2 seconds.

29. (Original)

AMENDMENT ---

8

Patent Application No. 10/712,196
Docket No. JSF02-0004

The method of claim 1, wherein said adhesive layer comprises Abocast 50-24 epoxy resin from Abatron, Incorporated, Kenosha, WI 53144 USA.

5

30. (New) A plurality of sealed micro enclosures on a substrate wafer, each enclosure is enclosed by:

(1) a top wafer bonded to said substrate wafer with an epoxy layer,

10

(2) a bottom formed from said substrate wafer, and

(3) a sidewall formed from at least one metal films,

wherein said metal films are prepared by sputtering or evaporation deposition processes, said sidewall surround

an island on said substrate wafer, and said island is

15

formed from layers comprising said top wafer and said epoxy layer.